

Technical Data 2078
Carbofol® Type HDPE 406 OIT
smooth/smooth

dated: 28.01.2008

Property	Test Method	Unit					
Thickness nominal -5%	ASTM D 5199	mm	1,00	1,50	2,00	2,50	3,00
Width	/	mm	9400	9400	9400	9400	9400
Density	ASTM D 1505 ASTM D 792	g/cm ³	0,942	0,942	0,942	0,942	0,942
Melt flow index	ASTM D 1238 Cond. P 190/5	g/10 min	< 3,0	< 3,0	< 3,0	< 3,0	< 3,0
Melt flow index	ASTM D 1238 Cond. E 190/2,16	g/10 min	< 1,0	< 1,0	< 1,0	< 1,0	< 1,0
Tensile strength at yield	ASTM D 6693	N/mm MPA	16 16	25 16	33 16	43 16	50 16
Elongation at yield	ASTM D 6693	%	12	12	12	12	12
Tensile strength at break	ASTM D 6693	N/mm MPA	28 > 26	45 > 26	60 > 26	80 > 26	90 > 26
Elongation at break	ASTM D 6693	%	700	700	700	700	700
Carbon black content	ASTM D 1603	%	2	2	2	2	2
Carbon black dispersion	ASTM D 5596	Category	1-2	1-2	1-2	1-2	1-2
Tear resistance	ASTM D 1004	N	130	200	280	350	450
Cold bending at -20°C	ASTM D 2136	—	passed	passed	passed	passed	passed
Multi axial elongation	Based on DIN 53861 / EN 14151	%	15	15	15	15	15
ESCR	ASTM D 1693	hours	2000	2000	2000	2000	2000
Perforation resistance	DIN 16726	mm	450	800	1200	1600	1800
Dimensional stability after warm storage 1h/100°C	ASTM D 1204	%	≤ 2	≤ 2	≤ 1	≤ 1	≤ 1
NCTL – Test	ASTM D 5397 app.	hours	> 300	> 300	> 300	> 300	> 300
OIT	ASTM D 3895	min	100	100	100	100	100
Puncture resistance	ASTM D 4833 EN ISO 12236	N	390 2600	500 4000	700 5400	820 6700	1000 7500

file: 2078 - 406 s-s OIT Rev.7 en.doc